

IN THE CLAIMS

Please amend the claims in accordance with the following rewritten claims in clean form. Applicant includes herewith an Attachment for Claim Amendments showing a marked up version of each amended claim. Note that the brackets [**] do not indicate deletions.

B 1
5
C 1

1. (Amended) Magnetic powder composed of an alloy composition represented by $R_x(Fe_{1-y}Co_y)_{100-x-z-w}B_zNb_w$ (where R is at least one rare-earth element, x is 7.1 – 9.9at%, y is 0 – 0.30, z is 4.6 – 6.9at%, and w is 0.2 – 3.5at%), the magnetic powder being constituted from a composite structure having a soft magnetic phase and a hard magnetic phase, wherein the magnetic powder has magnetic properties in which, when the magnetic powder is formed into an isotropic bonded magnet by mixing with a binding resin and then molding, the irreversible susceptibility (χ_{irr}) which is measured by using an intersection of a demagnetization curve in the J-H diagram representing the magnetic properties at room temperature and a straight line which passes through the origin in the J-H diagram and has a gradient (J/H) of $-3.8 \times 10^{-6} \text{H/m}$, as a starting point is equal to or less than $5.0 \times 10^{-7} \text{H/m}$, and the intrinsic coercive force (H_{cJ}) of the bonded magnet at room temperature is in the range of 320 – 720 kA/m.

2. (Amended) The magnetic powder as claimed in claim 1, wherein when the magnetic powder is formed into an isotropic bonded magnet having a density $\rho [\text{Mg/m}^3]$ by mixing with a binding resin and the molding the remanent magnetic flux

density $Br[T]$ at room temperature satisfies the relationship represented by the formula of $Br/\rho [\times 10^{-6} T \cdot m^3/g] \geq 0.125$.

3. (Amended) The magnetic powder as claimed in claim 1, wherein when the magnetic powder is formed into an isotropic bonded magnet by mixing with a binding resin and then molding the absolute value of the irreversible flux loss (initial flux loss) is equal to or less than 6.2%.

5. (Amended) The magnetic powder as claimed in claim 1, wherein said R includes Pr and a ratio of Pr with respect to the total mass of said R is 5 – 75%.

6. (Amended) The magnetic powder as claimed in claim 1, wherein said R includes Dy and a ratio of Dy with respect to the total mass of said R is equal to or less than 14%.

7. (Amended) The magnetic powder as claimed in claim 1, wherein the magnetic powder has been obtained by quenching the alloy in a molten state.

8. (Amended) The magnetic powder as claimed in claim 1, wherein the magnetic powder has been obtained by milling a melt spun ribbon of the alloy with a cooling roll.

9. (Amended) The magnetic powder as claimed in claim 1, wherein the magnetic powder has been subjected to a heat treatment for at least once during the manufacturing process or after manufacturing.

B2

Please cancel Claim 14 without prejudice or disclaimer of the subject matter contained therein.